

Latex Examination Gloves



Latex Exam Gloves

Confidence is key. When you see, smell and stretch a pair of our Latex Gloves, you will feel the quality and consistency that is inherent in all **DuraShield**™ gloves. Slip your hand into a pair, and you will quickly discover that these are gloves you can rely on for protection and comfort.

Sensi-Grip™ Lightly Powdered Latex Exam Gloves offer unsurpassed tactile sensitivity, dexterity, flexibility and tensile strength. These gloves are lightly powdered with a special low magnesium, biologically absorbable cornstarch to make donning easy, and all day wear comfortable. Using only the highest quality raw materials, each glove is chemically resistant to alkalis, acids, alcohols, and ketones. Smooth finish.

Sure-Grip™ Powder Free Latex Exam Gloves are tested twice to insure the highest possible quality, strength and flexibility. This ambidextrous glove provides ultimate protection against contamination and assures chemical resistance to acids, alkalis, alcohols, and ketones. Textured finish.

Applications: Medical, Dental, Laboratory, Industrial, Safety

Specifications

Tensile Properties

| | |
|------------------------------------|---------------------|
| <u>Puncture Resistance</u> | Not Less than 7.0 N |
| <u>Unaged</u> | |
| Tensile Strength (MPa)..... | Not Less than 21.0 |
| Elongation, %..... | Not Less than 700 |
| Permanent Deformation after | |
| 60%Elongation..... | Not Less than 8% |
| <u>Aged 70 +/- 2° C for 7 days</u> | |
| Tensile Strength (MPa)..... | Not Less than 17.6 |
| Elongation, %..... | Not Less than 500 |

*Specifications subject to change without notice.

Dimensions

| | |
|-------------------------------------|-----------------------|
| <u>Width</u> | |
| Extra Small..... | 75 / 5 mm |
| Small..... | 85 / 5 mm |
| Medium..... | 95 / 5 mm |
| Large..... | 106 / 5 mm |
| Extra Large..... | 116 / 5 mm |
| <u>Length</u> | Not Less than 240 mm |
| <u>Thickness (single wall)</u> | Not Less than 0.05 mm |



1505 Corporate Woods Pkwy, Suite 500
Uniontown, OH 44685
info@plxindustries.com

Local: 330-896-7373
Fax: 330-899-0407

800-978-4299

Latex Examination Gloves



Lightly Powdered Latex Exam Gloves

| Product No. | Description | Size | QTY/BOX | QTY/CS |
|-------------|---|---------|---------|--------|
| COAP100-XS | Lightly Powdered Latex Exam Gloves – 9” | X-Small | 100 | 1,000 |
| COAP200-S | Lightly Powdered Latex Exam Gloves – 9” | Small | 100 | 1,000 |
| COAP300-M | Lightly Powdered Latex Exam Gloves – 9” | Medium | 100 | 1,000 |
| COAP400-L | Lightly Powdered Latex Exam Gloves – 9” | Large | 100 | 1,000 |
| COAP500-XL | Lightly Powdered Latex Exam Gloves – 9” | X-Large | 100 | 1,000 |

***Non-Medical Also Available**

Powder Free Latex Exam Gloves

| Product No. | Description | Size | QTY/BOX | QTY/CS |
|-------------|------------------------------------|---------|---------|--------|
| COAP110-XS | Powder Free Latex Exam Gloves – 9” | X-Small | 100 | 1,000 |
| COAP220-S | Powder Free Latex Exam Gloves – 9” | Small | 100 | 1,000 |
| COAP330-M | Powder Free Latex Exam Gloves – 9” | Medium | 100 | 1,000 |
| COAP440-L | Powder Free Latex Exam Gloves – 9” | Large | 100 | 1,000 |
| COAP550-XL | Powder Free Latex Exam Gloves – 9” | X-Large | 100 | 1,000 |

***Non-Medical Also Available *12” Powder Free Latex Exam Gloves HIGH RISK Are Available**



| | |
|---|-----------------|
| Vinyl Exam Powder-Free | GLP0081 (S-XL) |
| Vinyl Exam 12” Powder Free | GLP0088 (S-XL) |
| Vinyl Exam Lightly Powdered | GLP0091 (S-XL) |
| Nitrile Exam Powder-Free | GLP0065 (S-XL) |
| Nitrile Exam Lightly Powdered | GLP0055 (XS-XL) |
| Latex Exam Powder-Free HIGH RISK 12” | GLP0110 (S-XL) |

CLEANROOM GLOVES ARE ALSO AVAILABLE

Local: 330-896-7373
 Fax: 330-899-0407
800-978-4299
www.plxindustries.org

PLX Industries INC.
Portage Lakes
INDUSTRIES

1505 Corporate Woods Pkwy, Suite 500
 Uniontown, OH 44685
info@plxindustries.com



LATEX GLOVE CHEMICAL RESISTANCE CHART

*Limited service | VG= Very Good | G= Good | F=Fair | P=Poor (not recommended)

| Chemical | Natural Latex or Rubber |
|-----------------------|-------------------------|
| *Acetaldehyde | G |
| Acetic acid | VG |
| *Acetone | VG |
| Ammonium hydroxide | VG |
| *Amyl acetate | P |
| Aniline | F |
| *Benzaldehyde | F |
| *Benzene | F |
| Butyl acetate | F |
| Butyl alcohol | VG |
| Carbon disulfide | F |
| *Carbon tetrachloride | P |
| Castor oil | P |
| *Chlorobenzene | P |
| *Chloroform | P |
| Chloronaphthalene | P |
| Chromic Acid (50%) | P |
| Citric acid (10%) | VG |
| Cyclohexanol | F |
| *Dibutyl phthalate | P |
| Diesel fuel | P |
| Diisobutyl ketone | F |
| Dimethylformamide | F |
| Diocetyl phthalate | P |
| Dioxane | G |
| Epoxy resins, dry | VG |
| *Ethyl acetate | F |
| Ethyl alcohol | VG |
| Ethyl ether | G |
| *Ethylene dichloride | P |
| Ethylene glycol | VG |
| Formaldehyde | VG |
| Formic acid | VG |
| Freon 11 | P |
| Freon 12 | P |
| Freon 21 | P |
| Freon 22 | P |
| *Furfural | G |
| Gasoline, leaded | P |
| Gasoline, unleaded | P |

Local: 330-896-7373
 Fax: 330-899-0407
800-978-4299
www.plxindustries.org

PLX Portage ^{INC}
 Lakes
INDUSTRIES

1505 Corporate Woods Pkwy, Suite 500
 Uniontown, OH 44685
info@plxindustries.com



| Chemical | Natural Latex or Rubber |
|---------------------------------|--|
| Glycerine | VG |
| Hexane | P |
| Hydrochloric acid | G |
| Hydrofluoric acid (48%) | G |
| Hydrogen peroxide (30%) | G |
| Hydroquinone | G |
| Isooctane | P |
| Isopropyl alcohol | VG |
| Kerosene | F |
| Ketones | VG |
| Lacquer thinners | F |
| Lactic acid (85%) | VG |
| Lauric acid (36%) | F |
| Linoleic acid | P |
| Linseed oil | P |
| Maleic acid | VG |
| Methyl alcohol | VG |
| Methylamine | F |
| Methyl bromide | F |
| *Methyl chloride | P |
| *Methyl ethyl ketone | G |
| *Methyl isobutyl ketone | F |
| Methyl methacrylate | G |
| Monoethanolamine | G |
| Morpholine | VG |
| Naphthalene | F |
| Naphthas, aliphatic | F |
| Naphthas, aromatic | P |
| *Nitric acid | F |
| Nitromethane (95.5%) | P |
| Nitropropane (95.5%) | P |
| Octyl alcohol | VG |
| Oleic acid | F |
| Oxalic acid | VG |
| Palmitic acid | VG |
| Perchloric acid (60%) | F |
| Perchloroethylene | P |
| Petroleum distillates (naphtha) | P |
| Phenol | F |
| Phosphoric acid | G |
| Potassium hydroxide | VG |
| Propyl acetate | F |
| Propyl alcohol | VG |
| Propyl alcohol (iso) | VG |
| Sodium hydroxide | VG |
| *Limited service | VG= Very Good G= Good F=Fair P=Poor (not recommended) |



Local: 330-896-7373
 Fax: 330-899-0407

800-978-4299
www.plxindustries.org

PLX Portage
 Lakes
 INDUSTRIES INC.

1505 Corporate Woods Pkwy, Suite 500
 Uniontown, OH 44685
info@plxindustries.com



| Chemical | Natural Latex or Rubber |
|----------------------|-------------------------|
| Styrene | P |
| Styrene (100%) | P |
| Sulfuric acid | G |
| Tannic acid (65%) | VG |
| Tetrahydrofuran | F |
| *Toluene | P |
| Toluene diisocyanate | G |
| *Trichloroethylene | F |
| Triethanolamine | G |
| Tung oil | P |
| Turpentine | F |
| *Xylene | P |

*Limited service VG= Very Good G= Good F=Fair P=Poor (not recommended)

Reference: Information obtained from <http://www.cdc.gov/od/ohs/manual/pprotect.htm>



Local: 330-896-7373
Fax: 330-899-0407
800-978-4299
www.plxindustries.org

PLX **INC.**
Portage Lakes
INDUSTRIES

1505 Corporate Woods Pkwy, Suite 500
Uniontown, OH 44685
info@plxindustries.com



MATERIAL SAFETY DATA SHEET

POWDER FREE LATEX GLOVES

Identification

Product Code: COAP110 COAP220 COAP330
 COAP440 COAP55 COAPNM215
 COAPNM315 COAPNM415 COAPNM515
 COAPT X220 COAPT X330 COAPT X440
 COAPT X550

Product Description: Powder Free Latex Glove

Normal Precautions

Single Use Only

This product is excellent for use as a *biological barrier* but is not to be used as a *chemical barrier*.

Exposure Data

Skin: Contains natural rubber latex which may cause allergic reactions in some people. Please consult physician should this occur.

Safe use of this product by or on latex sensitized individuals has not been established.

No Antimicrobial and/or Hypoallergenic claim is made on this product.

Other Precautions

Storage: Store in a cool, dry place.

Do not expose products under direct sunlight or fluorescent light.



PLX Portage ^{INC.}
Lakes
INDUSTRIES

800-978-4299

Local: 330-896-7373
Fax: 330-899-0407
www.plxindustries.org